



Scotchlite™ Removable Reflective Graphic Film with Comply™ Adhesive

IJ680CR-10, RG680CR-10* for Solvent, UV and Latex Inkjet Printing

1. Product Description

These 7-mil, removable, enclosed lens, retroreflective, engineer grade films feature flexibility and versatility with slideable, pressure-activated adhesive. Air release channels in the adhesive allow fast and easy, bubble-free graphic installation. Use these long-term durable films for commercial vehicle, sign and bus graphics and striping on vertical, flat, curved or corrugated surfaces, with or without rivets.

* Film RG680CR-10 is available for purchase and use with only a 3M Basic Product Warranty on a customer test and approve basis.

A. Advantages

- Comply adhesive featuring air release channels
- Up to 9 year expected performance life and up to 7 year 3M™ MCS™ Warranty on many applications
- Designed for excellent cutting and weeding with computer sign cutting equipment
- Similar daytime and nighttime appearance that retains most of its reflectivity when wet
- Excellent angularity
- Unprocessed film resists fuel vapors or occasional spills

2. Recommended Types of Graphics and End Uses

When constructed and used as described in this Bulletin, these types of graphics and end uses may be warranted by the 3M™ MCS™ Warranty or the 3M Performance Guarantee. Please read the entire Bulletin for details.

- Vertical fleet truck and trailer, commercial vehicle and bus graphics, railcars
- Vertical commercial signs and striping
- Vertical indoor and outdoor signage

A. Limitations of End Uses

This 3M product is not designed or recommended for the following uses. Please contact us to discuss other options.

(1) Unsuitable End Uses for This Film

- Do not apply this film on:
 - Walls
 - Substrates with compound curves
 - Substrates that do not have a clean, smooth surface or have poor paint-to-substrate adhesion
 - Stainless steel
 - FRP with a Tedlar® coating
 - Flexible substrates
- Paint that is not thoroughly cured or dried.
- Low surface energy substrates (some plastics, powder-coated paints, etc.)
- Also see limitations of graphic removal, page 6.

3. Compatible Products

This Bulletin provides details about the base film, recommended construction options, warranted durability and warranty limitations for the constructions shown in the **Warranted Durability Tables**. Additional specific information about compatible products can be found in the Product and Instruction Bulletins listed in **3M Related Literature** at the end of this bulletin.

See the Warranty matrix to determine which Compatible Products are approved for your graphic construction.

A. Solvent Inkjet Inks and Printers

Ink Series

- 3M™ Piezo Inkjet Ink Series 1500v2
- 3M™ Piezo Inkjet Ink Series 4400
- 3M™ Piezo Inkjet Ink Series 4800
- 3M™ Piezo Inkjet Ink Series 6200

Printer

EFI™ VUTEK® 150, 2360/3360, 3300/5300 & 3000/5000 Printers
 HP XLJet Series 1200, 1500 Printers
 HP Scitex TJ8300 Series Digital Press
 Agfa .Jeti 3312, 3318, 3324, 5024 [Gandinovations] Printers

B. Latex Inkjet Inks and Printers

- HP 3M LX600 Specialty Latex Ink

HP Designjet L65500, Scitex LX600 & LX800

C. UV Inkjet Inks and Printers

- 3M™ Piezo Inkjet UV Ink Series 2200UV
- 3M™ Piezo Inkjet UV Ink Series 2600UVv2
- 3M™ Piezo Inkjet UV Ink Series 2700UV
- 3M™ Piezo Inkjet UV Ink Series 2800UV
- 3M™ Piezo Inkjet Ink Series 5400UV
- GSr 3M™ Premium UV Inks
- Mimaki Ink Series LF-200 *Manufactured by 3M*

EFI™ VUTEK® PV200 Printer
 3M™ Printer 2500UV
 Durst Rho 160R & 351R Printers
 EFI™ VUTEK® QS2000, QS3200, QS3220 and QS220 Printers
 HP Designjet H35000/H45000
 EFI™ VUTEK® GS5000r Printer
 Mimaki UJV-160, JFX-1631 & 1615R Printer

D. Graphic Protection

- 3M™ Screen Print Gloss Clear 1920DR
- 3M™ Screen Print UV Gloss Clear 9720i
- 3M™ Screen Print Gloss Clear 9720UV
- 3M™ Scotchcal™ Gloss Overlamine 8518
- 3M™ Scotchcal™ Luster Overlamine 8519

E. Other Products

- 3M™ Prespacing Tape SCPM-53X
- 3M™ Prespacing Tape SCPS-55
- 3M™ Premasking Tape SCPM-3
- 3M™ Premasking Tape SCPM-44X

4. Characteristics

These are typical values for unprocessed product; processing may change the values. Contact your 3M representative for a custom specification.

A. Physical Characteristics

Characteristic	Value
Material	Vinyl
Thickness	With adhesive: 7 to 8 mils (0.18 to 0.20 mm)
Film number & color	IJ680CR-10, RG680CR-10: White
Retroreflectivity <i>typical</i>	<ul style="list-style-type: none"> • Meets ASTM D 4956-07, Type 1 • 100 candlepower at -4° entrance angle and 0.2° observation angle.

Continued on the next page

Characteristic	Value
Retroreflection Definition	The typical coefficient of retroreflection defined is measured at a -4° entrance angle and a 0.2° observation angle. It is expressed in candlepower per foot-candle per square foot (candela/lux/square meter) per ASTM E 810. The entrance angle is formed by a light beam striking the surface at a point and a line that is perpendicular to the surface at the same point. An observation angle is formed by the light beam striking the reflective surface and returning to the observer. From 800 feet (249 meters), a motorist normally views a graphic at a 0.2° angle.
Adhesive type	Pressure-activated, slideable, with air release channels
Adhesive color	White
Liner	Polyethylene-coated paper
Safety Standards	See Section 13. for ASTM, NFPA and AAR information.
Chemical resistance	<ul style="list-style-type: none"> Resists mild alkalis, mild acids, and salt Excellent resistance to rain (<i>not immersion</i>) Resists occasional fuel spills
Flammability	Call 1-800-328-3908 for information

B. Application Characteristics

Characteristic	Value
Finished graphic application recommendation	Surface type: Flat, with/without rivets; moderate curves; corrugations Substrate type: Aluminum, FRP, paint Graphic orientation: Vertical only Application method: Dry
Application temperature	Application temperature: <i>air and substrate</i> <ul style="list-style-type: none"> 40° to 100°F (4° to 38°C) flat surfaces without rivets 45° to 100°F (7° to 38°C) flat, curved or corrugated surfaces with rivets
Adhesion 24 hours after application	Aluminum: 4.8 lb/in (0.86 kg/cm) FRP (Fiberglass Reinforced Plywood): 3.7 lb/in (0.7 kg/cm) Painted aluminum panels: 2.6 pounds/inch (0.5 kg/cm)
In use temperature range	-30° to +200°F (-34° to +93°C)

5. Definitions

A. Exposure

U.S. Vertical Exposure



face of graphic

The face of the graphic is +/- 10° from vertical.

U.S. Desert Southwest Exposure

Any outdoor graphic exposed to solar energy more than half of the daylight hours in Arizona, New Mexico and the desert areas of California, Nevada, Utah and Texas is subject to reduced warranties. A detailed map is available at 3Mgraphics.com under Warranties.

B. Graphic Types

Indoor Signs

Stationary graphics applied indoors and *not* exposed to the elements.

Outdoor Signs

Stationary graphics applied outdoors and exposed to the elements.

OEM

Labels and decorative graphics produced for and used by original equipment manufacturers.

C. Vehicle Types

Commercial Vehicle

Buses, vans, automobiles, trucks and trailers (except those defined as Fleet Trucks and Trailers) that are used for commercial business purposes

Fleet Trucks and Trailers

Straight trucks, semi-tractors and trailers used in commercial fleets. Excludes air shields.

Personal Vehicle

Vans, automobiles, pickup trucks and trailers primarily for personal use.

Recreational Vehicle (RV)

Vehicles used for personal pleasure, such as campers, motor homes and trailers, that are not used in connection with any commercial or business enterprise. 3M specifically excludes watercraft from this definition.

Railcars

Rail cars and lead cars, but not locomotives or engines.

Locomotives, Engines

Please contact us to discuss your needs.

D. Graphic Construction

The products used to make a graphic, which may include film and/or flexible substrate, graphic protection, ink, printer and application tape.

E. Graphic Protection

Overlamine films or clear coats used to protect the graphic and/or change gloss.

F. Removable with Heat

Film is removable when heat is used within the specified time period and leaves no more than 10% adhesive residue on flat and simple curves without rivets, and no more than 30% adhesive residue on rivets and/or corrugations.

6. Warranty Information

A. Limitations and Disclaimers Applicable to All Warranties & Warranty Coverage Overview

Both the warranty coverage and the durability for each graphic is based on the user(s) reading and following all applicable and current [3M Product and Instruction Bulletins](#). 3M will honor the Warranted Durability stated in the base film or substrate Product Bulletin that is current when the film was purchased. Warranted durabilities may be reduced and stipulations may apply for certain constructions and applications, as covered in this Bulletin.

The following is made in lieu of all other express or implied warranties, including any implied warranty of **merchantability** or fitness for a particular purpose or implied warranty arising out of a course of dealing, custom or usage of trade. 3M will replace or refund the price of any 3M materials that do not meet this warranty within the specified time periods. These remedies are exclusive. **In no case shall 3M be liable for any direct, indirect, or consequential damages, including any labor or non-3M materials charges.**

See the [3M Warranty Brochure](#) at 3Mgraphics.com, which gives the terms, additional limitations of the warranty, if any, and limitations of liability.

B. 3M Basic Product Warranty

All 3M products are warranted to be free of defects in materials and manufacture at the time of shipment and to meet the specifications stated in this Product Bulletin and as further set forth in the [3M Warranty Brochure](#).

C. 3M™ MCS™ Warranty

Subject to Stipulations set forth in Section E., below

Finished graphics constructed with the materials specified and the exposure specified in the Warranted Durability Tables, Section C.(1), are eligible for the 3M™ MCS™ Warranty. For warranties for other exposures, see Section E.(1).

(1) Warranted Durability Table for Finished Graphics in a Standard U.S. Vertical Exposure

- VEH = Commercial Vehicle, Fleet Truck and Trailer, Bus Graphics
- RAIL = Railcar Graphics
- OUT = Outdoor Signs
- IN = Indoor Signs

Warranted Durability for Finished Graphics, In Years

	EFI™ VUTEK® 150, 2360/ 3360, 3300/5300, 3000/5000				HP XLJet Series 1200, 1500				HP Scitex TJ8300 and TJ8350 Digital Presses			
	SOLVENT Ink Series 1500v2				SOLVENT Ink Series 4400				SOLVENT Ink Series 4800			
Graphic Protection	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN
8518, 8519	7	4	4	8	7	4	4	8	7	4	4	8
1920DR	3	3	3	5	—	—	—	—	3	3	3	5
9720UV	—	—	—	—	—	—	—	—	3	3	3	5
9720i	5	4	4	8	5	4	4	8	5	4	4	8
None	—	2	—	3	—	2	—	3	—	2	—	3

	Agfa [Gandinnovations] .Jeti 3312, 3318, 3324, 5024				HP Designjet L65500; Scitex LX600 & LX800 Printers				EFI™ VUTEK® GS500r Printer			
	SOLVENT Ink Series 6200				HP 3M LX600 Specialty Latex Ink				GSr 3M™ Premium UV Inks			
Graphic Protection	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN
8518, 8519	7	4	4	8	4	3	—	5	5	4	4	8
1920DR	5	4	4	8	2	2	—	2	3	2	—	5
9720i	5	4	4	8	—	—	—	—	4	3	3	8
None	—	3	—	3	—	—	—	—	—	2	—	3

	EFI™ VUTEK® PV200				3M™ Printer 2500UV				Durst Rho 160R & 351R			
	Ink Series 2200UV				Ink Series 2600UVv2				Ink Series 2700UV			
Graphic Protection	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN
8518, 8519	7	4	4	8	7	4	4	8	7	4	4	8
1920DR	—	—	—	—	5	4	4	8	—	—	—	—
9720i, 9720UV	5	4	4	8	5	4	4	8	5	4	4	8
None	—	3	—	3	—	3	—	3	—	3	—	3

	VUTEK® QS2000, QS3200, QS3220, QS220				HP Designjet H35000/45000				Mimaki UJV-160, JFX-1631 & 1615R			
	Ink Series 2800UV				Ink Series 5400UV				Ink Series LF-200			
Graphic Protection	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN	VEH	OUT	RAIL	IN
8518, 8519	7	4	4	8	7	4	4	8	7	4	4	8
9720i, 9720UV	5	4	4	8	5	4	4	8	—	—	—	—
None	—	3	—	3	—	3	—	3	—	—	—	—

(2) Unprinted Film with No Graphic Protection, and a U.S. Vertical Exposure

For unprinted film, 3M offers:

- Warranted Durability for finished graphics covered by the 3M™ MCS™ Warranty.
- Expected Performance Life as a good faith estimate of how long unprinted product may perform satisfactorily based on 3M testing. However, there is no warranty for performance or durability.

	Years		
	Ink and Graphic Protection	VEH	OUT
3M™ MCS™ Warranty Durability	None	7	7
Expected Performance Life, Unwarranted	None	9	9

(3) Removal Warranty with Heat or Chemicals

Within the stated warranted durability period of each graphic construction in this Bulletin, if this film cannot be removed with heat and/or chemicals, or if more than 30% of the adhesive residue remains on the substrate, 3M will reimburse a reasonable portion of extra removal costs.

a. Removal Warranty Exceptions

The following exceptions are not covered by the Removal Warranty.

- Substrate damage due to:
 - removing film from a pre-existing graphic
 - removing film that was applied to painted wallboard
 - removing film from paint that is not firmly bonded to the substrate
- No guarantee is made for:
 - ease or speed of removal of any graphic
 - removal from railroad cars or engines, or stainless steel or bare aluminum
 - removal from paint that is improperly cured
 - removal from aged paint or metals, surface oxidation or chalking; user must test, approve and accept liability for such applications

b. Removal Factors

The ease and rate of removal using heat depends on several factors. Also see Instruction Bulletin 6.5.

- Substrate type and condition
- Graphic age and weathering conditions
- Removal is performed when the air and surface temperature is above 60°F (15°C)
- Angle of removal, which should be less than 90 degrees

D. 3M Performance Guarantee

Subject to Stipulations set forth in Section E., below

Graphics constructed with the 3M materials specified and in the exposure specified in the Warranted Durability Table, Section D.(1), are eligible for the 3M Performance Guarantee. This warranty only covers the performance of the recommended 3M products used in the graphic construction when imaged with the printers and OEM inks listed in the most current version of [Performance Guarantee Matrix](#) at 3Mgraphics.com. The Matrix may also list certain restrictions for using the film covered in this Bulletin. For warranties for other exposures, see Section E.(1).

Warranted Durability for 3M Product Performance Only, in Years

(1) Warranted Durability Table for

- 3M Product Performance
- Standard U.S. Vertical Exposure

Film	Graphic Protection	Vehicles & Outdoor	Indoor	Inks and Printers
IJ680CR-10	8518 8519 1920DR 9720i 9720UV	2	4	See the Performance Guarantee Matrix

E. General Warranty Stipulations for 3M™ MCS™ Warranty and 3M Performance Guarantee

These stipulations apply to both the 3M™ MCS™ Warranty and 3M Performance Guarantee unless otherwise noted. Specific provisions of these stipulations are covered in the [3M Warranty Brochure](#) at 3Mgraphics.com.

(1) Reduced Warranted Durability for Selected Graphic Exposures

For each exposure shown below, multiply the warranted durability years for your graphic construction as shown in the applicable Warranted Durability Tables, Section C.(1) or Section D.1, by the percentage shown for the intended graphic exposure. This is the reduced warranty.

If the Outdoor Graphic Exposure is:	Use this Percentage of U.S. Vertical Exposure, Warranted Durability	Examples
Desert Southwest Vertical	70% (0.7)	0.7 x 5 years = 3.5 years 0.7 x 2 years = 1.4 years
Non-vertical	0	0

(2) Reduced Warranty for Graphics Exposed to Heat

Long exposure to continuous high heat decreases the durability of this film by 2 years. High heat is a temperature above 150°F (65°C). It may occur in areas such as railroad locomotives, vehicle engine compartments, non-insulated tankers exposed to frequent internal steam cleaning, or compartments that carry hot cargo.

- (3) **Abrasion and Loss of Gloss** Abrasion damage and loss of gloss are not covered by any 3M warranty. This is considered normal wear and tear.
- (4) **Application to Glass** 3M accepts no liability for glass breakage when using this film for window graphics. See [Instruction Bulletin 5.1](#) for details.
- (5) **Application Outside the U.S.** Contact the 3M organization for that country.
- (6) **Graphics Made with Components Not Sold or Recommended by 3M** The 3M™ MCS™ Warranty does not cover finished graphics made with inks, film, graphic protection and/or application tapes that are not sold or recommended by 3M. The user is solely responsible for the graphic appearance, performance and durability of graphic constructions that include any other products.

The 3M Performance Guarantee covers selected 3M branded graphics products when used with qualified printers and inks.
- (7) **Graphic Protection** Any graphic exposed to abrasive conditions (including vehicles), harsh cleaners or chemicals must include graphic protection in order to be warranted. Abrasion damage and gloss loss are not covered.
- (8) **Rivets** This film may tent when applied over rivets. If the rivets are closely spaced, the film will likely bridge between rivets. Tented or bridged film may fail prematurely, which is not covered by any 3M warranty.

7. Factors that Affect Graphic Performance Life

The actual performance life of a graphic is affected by all of the following.

- The combination of graphics materials used
- Adequate ink drying or curing
- Selection, condition and preparation of the substrate
- Surface texture
- Application methods
- Angle and direction of sun exposure
- Environmental conditions
- Cleaning or maintenance methods

8. Graphics Manufacturing



CAUTION

Before using any equipment, always follow the manufacturers' instructions for safe operation.

A. Inkjet Printing

Always read and follow the ink manufacturer's written instructions on usage.

(1) Total Ink Coverage

250% is the maximum recommended total ink coverage for this film for all solvent, latex and UV inks.

Too high a total physical ink amount on the film results in media characteristic changes, inadequate drying, overlamine lifting, and/or poor graphic performance. Make sure that the ink lay down is within the limits of what the dryer can handle to prevent ink smearing. The Product & Instruction Bulletin for each 3M ink series includes additional details about total ink coverage.

Note: Be sure to check the consistency of color on reflective film as it may appear different in daytime and nighttime lighting.

(2) Adequately Dry Graphics

Important Note!

Inadequate drying can result in graphic failure including curling, increased shrinkage and adhesion failure, which are not covered under warranty.

Always build enough time into your process to ensure adequate drying of the graphic. Poorly dried film may become soft and stretchy, and the adhesive may become too aggressive. This can cause difficulty when applying an overlamine, rolling or applying the graphic. See the ink's Instruction Bulletin for more details.

B. Cutting

(1) Methods

The following are common cutting methods for this film. See [Instruction Bulletin 4.1](#) for details.

- Cold and hot steel-ruled die cutting
- Hot kiss cutting
- Drum-type electronic cutting
- Flat-bed electronic cutting
- Guillotine
- Hand cut

(2) Design Considerations

- Use a minimum letter height of 1 inch (2.5 cm).
- Use a minimum stroke width of 3/8 inch (1.0 cm).
- Use a minimum radius for a point of 1/16 inch (1.6 mm).
- For uniform color and brightness when making a graphic with multiple pieces of the film together, be sure the pieces are properly color matched. See [Instruction Bulletin 2.1](#) for details. Color-matched white film is available by special order at no extra charge. Contact your 3M sales representative.
- Order "roll applicator splices" for roll striping. Butt splices may have a small gap.

(3) Weeding Considerations

- For the best results, weed the film within 24 hours of cutting it.
- Perform weeding carefully. Removing the film from the liner reduces or may eliminate the slideability feature and air release feature.
- Refer to [Instruction Bulletin 4.1](#) for more details.

C. Liner Exchanging

Do not attempt to exchange the liner. This will compromise the slideability and air release channels of the film, and could negatively impact adhesion or appearance of the applied graphic, which is not covered by any 3M warranty.

D. Application Tapes

(1) When to Use Premasking Tape

- As an application aid to increase stiffness, and prevent stretching and damage during application.
- Graphics larger than 4 square feet (0.4 m²).
- Striping greater than 4 inches (10 cm) wide.

(2) When NOT to Use Premasking Tape

- Continuous rolls or striping wider than 12 inches (31 cm).
- Rolls wider than 12 inches (31 cm) that will be slit.

(3) When to Use Prespacing Tape

- Hold cut and weeded letters or graphics in registration after removing the film liner.
- Protect cut graphic parts from scratching or damage during application.
- Use when large amounts of liner are exposed.

(4) How to Select an Application Tape

Determine whether you want to premask the graphic or prespace cut graphics. Then select the application tape that corresponds to the graphic protection used. See [Instruction Bulletin 4.3](#) for complete details.

Graphic Protection Refer to the Warranty table to determine what graphic protection is approved for your graphic construction.

Application Tape	None	8518 8519 8528	1920DR	9720i 9720UV
Premasking Tape SCPM-3	■ ¹	■	■	
Premasking Tape SCPM-44X	■ ²			■
Prespacing Tape SCPS-55	■	■	■	■

1. All solvent inks.

2. All UV inks.

E. Handling Prespaced Graphics

For the best results when using prespacing tape SCPS-55, we recommend these practices:

- Store and ship prespaced film lying flat (do not roll it). This allows adhesion to build and minimizes the chance of the prespacing tape popping off of the liner or film.
- Handle the prespaced graphic as little as possible and keep it flat during processing.
- Remove as much liner as possible.

9. Application and Installation

Install the film using the dry application method.

Refer to the 3M Related Literature section, located at the end of this bulletin, for a list of the Instruction Bulletins that may be needed to apply or install this film.

A. Adhesive

This film has a pressure-activated adhesive that allows the film to slide easily on the substrate. Any pressure applied by hand, squeegee or application tool immediately bonds the film to the substrate and the slideability feature is lost. The film cannot be lifted and repositioned without damage.

Solvent from solvent-based ink that has not completely dried also affects slideability.

These films have air release channels, a characteristic of Comply adhesive.

Always work from the center out to the edges of the graphic to allow trapped air to exit through the air release channels. If the channels are closed off by firm pressure and air is trapped, use an air release tool to aid in removing air bubbles. See [Instruction Bulletin 5.4](#) for details.

B. Substrate Considerations

Some substrates such as under-cured polyurethane paint, fiberglass and some paint systems may continue to outgas for some time. Two-part polyurethane paints and screen print clears may stop curing when the air and surface temperatures are lower than 75°F (24°C). This film shows an ability to minimize bubbles due to outgassing.

This film is not recommended for use on low surface energy substrates such as some plastics, powder-coated paint, etc. The user must assume responsibility for testing and approving these substrates.

This film can be applied over other recommended 3M graphic systems. Graphics printed with clear 192ODR must be weathered for at least one year before applying this film over it. See [Instruction Bulletin 5.1](#) for details.

C. Graphics Printed with UV Inkjet Inks are Heat Sensitive!

UV inkjet inks may crack if too much heat is used during graphic application to complex curves and deep contours as well as around rivets. When using a heat gun or other heat source during application, make sure the film surface temperature does not exceed 212°F (100°C).

Using additional heat in the post-application process may cause UV inkjet ink to crack.

For the best results ***always do a test application*** of a UV inkjet printed graphic to determine how much heat can be used without damaging the image.

D. Finishing

- If needed or recommended, use edge sealer 3950.
- Most graphics made with these films do not require an edge sealer, although certain applications may benefit from its use.
- All processed and unprocessed graphics subjected to fuel vapors or occasional fuel spills do require edge sealer.
- Edge sealing in the following applications is not required, but it may help keep the edges adhered when subjected to external sources such as abrasion and/or high pressure washing.
 - graphics exposed to severe abrasion or high pressure washing
 - graphics applied to chrome substrates
 - graphics applied to locomotives and rolling railroad stock
 - graphics applied to truck rollup doors

10. Maintenance and Cleaning

Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline.)

Refer to [Instruction Bulletin 6.5](#) for details on pressure cleaning. Exceeding 3M's recommendations will void the warranty whether or not an edge sealer was properly used.

11. Removal

These films are removable with heat from most substrates within the warranted durability period specified for your construction. See [Instruction Bulletin 6.5](#) for details on how to remove graphics.

12. Shelf Life, Storage and Shipping

A. Shelf Life

Total shelf life: 3 years from the date of manufacture on the original box. Up to 3 years unprocessed, **OR** process within 2 years **and** then apply within 1 year of processing.

B. Storage Conditions

for Unprocessed Film or
Unapplied Finished Graphics

- 40° to 100°F (4° to 38°C)
- Out of sunlight
- Clean dry area
- Store unprocessed film in original container
- Cut sheets must lie flat
- Bring the film to print room temperature before using

C. Shipping Finished Graphics

Film with prespaced graphics using prespacing tape SCPS-55 applied: Flat only

All other constructions: Flat, or rolled printed side out on 6 inch (15 cm) or larger core. This helps prevent the application tape, if used, from popping off.

See [Instruction Bulletin 6.5](#) for details.

13. Health and Safety



CAUTION

When handling any chemical products, read the manufacturers' container labels and the Material Safety Data Sheets (MSDS) for important health, safety and environmental information. To obtain MSDS sheets for 3M products go to 3M.com/MSDS, or by mail or in case of an emergency, call 1-800-364-3577 or 1-651-737-6501.

When using any equipment, always follow the manufacturers' instructions for safe operation.

A. Standards

This information is important for applications that are regulated by ASTM or NFPA standards, for example, traffic control signs, emergency vehicles and certain railroad graphics. The user is solely responsible for determining and complying with all current and applicable local, state and federal regulations regarding the use and application of graphics materials.

B. ASTM D-4956-07: Standard Specification for Retroreflective Sheeting for Traffic Control

ASTM D-4956-07 covers flexible, non-exposed glass bead lenses and microprismatic retroreflective sheeting designed for use on traffic control signs, delineators, barricades and other devices. As defined in ASTM D-4956-07, film IJ680CR-10 (white) is classified as Type I sheeting (section 4.2.1) with a Class 3 adhesive (section 4.3.3). Film IJ680CR-10 (white) meets the requirements specified in section 6.1.1 (minimum performance requirements for Type I sheeting).

C. NFPA® 1901: Standard for Automotive Fire Apparatus (2009 Edition)

According to NFPA® 1901, section 15.9.3.3 specifies that all retroreflective materials required by section 15.9.3.1 and 15.9.3.2 shall conform to the requirements of ASTM D 4956, *Standard Specification for Retroreflective Sheeting for Traffic Control*, Section 6.1.1 for Type I sheeting. Film IJ680CR-10 (white) meets the requirements of NFPA 1901, Section 15.9.3.1 (Front and Sides).

D. AAR: Standard and Recommended Practices

This product is approved for use by the Association of American Railroads (AAR), Safety and Operations, as listed in the Manual of Standards and Recommended Practices, Section L - Lettering and Marking of Cars, Specification M-947, Adhesive-Backed Films.

14. 3M Related Literature

Before starting any job, be sure you have the most current Product and Instruction Bulletins.

The information in 3M Product and Instruction Bulletins is subject to change. [Current Bulletins](#) are available at 3Mgraphics.com. The following applicable Bulletins provide information and processes you need to properly make the graphics described in this Bulletin. Additional Bulletins may be needed as indicated in the 3M Related Literature section of other 3M components you use.

Bulletin types: PB = Product Bulletin; PB-IB = Product & Instruction Bulletin; IB = Instruction Bulletin

Subject	Type	Bulletin No.
3M™ Piezo Inkjet Ink Series 1500v2	PB-IB	1500
3M™ Piezo Inkjet Ink Series 4400	PB-IB	4400
3M™ Piezo Inkjet Ink Series 4800	PB-IB	4800
3M™ Piezo Inkjet Ink Series 6200	PB-IB	6200
3M™ Piezo Inkjet UV Ink Series 2200UV	PB-IB	2200UV
3M™ Piezo Inkjet UV Ink Series 2600UVv2	PB-IB	2600UVv2
3M™ Piezo Inkjet UV Ink Series 2700UV	PB-IB	2700UV
3M™ Piezo Inkjet UV Ink Series 2800UV	PB-IB	2800UV
3M™ Piezo Inkjet Ink Series 5400UV	PB-IB	5400UV
GSr 3M™ Premium UV Inks	PB-IB	GSr
Mimaki Ink Series LF-200 <i>Manufactured by 3M</i>	PB-IB	LF200
3M Graphic Protection Products	PB	GP-1
3M™ Screen Print UV Clears 9720i, 9720UV, 9730UV	PB-IB	Clears 9720
3M™ Screen Printing Ink Series 1900 and Clear 1920DR - Screen printing with ink series 1900- line color	PB IB	1900 3.12
Cold roll lamination	IB	4.22
Design of graphics	IB	2.1
Edge Sealer 3950 and 4150S, Edge Sealer Tape 8914	PB-IB	Edge Sealers
Scoring and cutting	IB	4.1
Using 3M application tapes; premasking and prespacing for films	IB	4.3
Application, substrate selection, preparation, substrate-specific techniques	IB	5.1
Application, special applications and vehicles	IB	5.4
Application, general procedures for indoor and outdoor dry applications	IB	5.5
Applicator's quick reference guide for vehicle film	IB	5.35
Storage, handling, maintenance, removal	IB	6.5
3M Warranty Brochure	go to www.3Mgraphics.com , Warranties	

3M, Controltac, Comply, MCS, Scotchcal, Scotchprint and Scotchlite, some or all of which may be mentioned in this Bulletin, are trademarks or registered trademarks of 3M Company.

NFPA is a registered trademark of National Fire Protection Association, Inc; EFI is a trademark and VUTEk is a registered trademark of EFI Inc.; Designjet is a trademark of Hewlett Packard Company; Tedlar is a registered trademark of DuPont Co. All other trademarks are the property of their respective owners.

15. Bulletin Change Summary

Correction made to 3M™ MCS™ Warranted Durability table for ink series GSr to remove clear 9720UV, which is NOT warranted for use with this ink series. Added Bulletin for GSr ink series to 3M Related Literature.



Commercial Graphics Division
3M Center, Building 220-12E-04
PO Box 33220
St. Paul, MN 55144-3220 USA
General Info. 1-800-374-6772
Technical Info. 1-800-328-3908
Fax 1-651-736-4233

3M Canada
P.O. Box 5757
London, Ontario
Canada N6A 4T1
1-800-265-1840
Fax 519-452-6245

3M México, S.A. de C.V
Av. Santa Fe No. 55
Col. Santa Fe, Del. Alvaro Obregón
México, D.F. 01210
52-55-52-70-04-00
Fax 52-55-52-70-22-77

3M Puerto Rico, Inc.
Puerto Rico Industrial Park
350 Chardon Avenue, Suite 1100
San Juan PR 00918
787-620-3000
Fax 787-620-3018

www.3Mgraphics.com

©3M 2011. All rights reserved.